




Revision Date: July 2016  
Version: 1.0

## GC OB-KSN

2-[4-[4-(2-Benzoxazolyl)styryl]phenyl]-5-methylbenzoxazole



Chemical Formula	C <sub>29</sub> H <sub>20</sub> N <sub>2</sub> O <sub>2</sub>
Molecular Weight	428.48
CAS	5242-49-9

GC OB-KSN is suitable for such trades as synthetic fibers, plastics, coating, paint, printing ink, etc, for brightening and blooming. It does not react with foaming agent and crosslinking agent, does not transfer. Suitable for brightening the polyester, polyamide, polypropylene and wool fabric. It can be used in any process segments of film injection molding, hot compacting material and high polymerized synthetic material.

---

### PHYSYCO-CHEMICAL PROPERTIES

Appearance	light yellow Powder
Content	99.0%min
Volatiles	0.5%max
Melting Point	335-345°C

**HANDLING AND STORAGE:** The processing and use of GC OB-KSN requires adequate technical and professional knowledge. Please consult safety data sheet for further handling, storage and toxicity information.

GC OB-KSN has to be stored in tightly sealed original container in a cool and well-ventilated area, away from direct sunlight.

**PACKAGING:** Standard pack size of GC OB-KSN is 25Kg in fiber drum.

### NOTE:

Information contained in this document is provided to the best of our knowledge and is considered true as per revision date. We do not accept any liability for loss and damage that may occur from the improper use of this information and for the use against the safety legal requirements and patent rights. This specification does not release the customer from the obligation to check the product as to its suitability for intended area of usage.