

Revision Date: December 2021 Version: 2.0

GC UV 3049

2,2'-dihydroxy-4,4'-dimethoxybenzophenone

Phone: +39 0362 1547305

Fax: +39 039 8942754

GC UV-3049 is an efficient UV absorber for polyester film, which it protests from premature damage, particularly under severe exposure conditions. The polyester film can be treated by applying a hot solution of it in a polyhydric alcohol.

PHYSICAL-CHEMICAL PROPERTIES

Appearance Light yellow powder

Assay (HPLC), % Min. 98 Trasmittance @500 nm, % Min. 95

HANDLING AND STORAGE: The processing and use of GC UV 3049 requires adequate technical and professional

knowledge. Please consult safety data sheet for further handling, storage and toxicity information. GC UV 3049 has to be stored in tightly sealed original container in a cool and

well-ventilated area, away from direct sunlight.

PACKAGING: Standard packaging size of GC UV 3049 is 25 Kg in fiber drum.

IMPORTANT NOTE Some plastic additives, fillers or pigments can have a significant influence on UV properties

of the end product. Before using this product, please be informed. Machine stop at high temperature could create degradation of polymers. Please clean with neutral polymers.

DISCLAIMER:

Information contained in this document is provided to the best of our knowledge and is considered true as per revision date. We do not accept any liability for loss and damage that may occur from the improperly use of this information and for the use against the safety legal requirements and patent rights. This specification does not release the customer from the obligation to check the product as to its suitability for intended area of usage.