



Revision Date: September 2018
Version: 1.1

MB SAN DETO 41 HALOGENATED FR MASTERBATCH

MB SAN DETO 41 is a masterbatch in a matrix of SAN that is heat-stable and synergized with a high content of bromine, making it the perfect candidate for processing at high temperature and stress conditions. MB SAN DETO 41 has a high UV resistance and a total absence of blooming effect. MB SAN DETO 41 finds its application mainly in ABS.

PHISYCAL-CHEMICAL PROPERTIES

Appearance	White Granules
Active Principle, %	75.0 min
Apparent Density	1.0 min
Ashes, %	5.0 max
Thermal stability, °C	280.0
Umidity, %	0.2 max

HANDLING AND STORAGE: The processing and use of MB SAN DETO 41 requires adequate technical and professional knowledge. Please consult safety data sheet for further handling, storage and toxicity information. MB SAN DETO 41 has to be stored in tightly sealed original container in a cool and well-ventilated area, away from direct sunlight

PACKAGING: Standard packaging size of MB SAN DETO 41 is 25 Kg in plastic bags

Important note

Some plastic additives, fillers or pigments can influence significantly the flame retardant properties of the end product. Before using this product, please be informed.

Machine stop at high temperature could create a degradation of polymers. Please clean with neutral polymers.

Disclaimer:

Information contained in this document is provided to the best of our knowledge and is considered true as per revision date. We do not accept any liability for loss and damage that may occur from the improperly use of this information and for the use against the safety legal requirements and patent rights. This specification does not release the customer from the obligation to check the product as to its suitability for intended area of usage.